

CLAIMS

What is claimed is :

- 5 1. A binder for electrode materials which comprises tetrafluoroethylene based polymer fine particles having an average particle size of not more than about 0.20 μm and having a standard specific gravity of not more than about 2.20, wherein a mixture prepared from said fine particles with about 17% by weight of the total mixture of an extrusion
- 10 coagent, when subjected to the measurement of an extrusion pressure by a rheometer, exhibits under the conditions of a draw ratio of 100 to 1 and an extrusion speed of 18 ± 2 mm/min, an extrusion pressure of not less than about 220 kg/cm².
- 15 2. A binder for electrode materials as set forth in Claim 1, wherein said tetrafluoroethylene based polymer is polytetrafluoroethylene or a copolymer of tetrafluoroethylene with at least one comonomer selected from the group consisting of fluoro(alkyl vinyl ethers) represented by formula $\text{CF}_3\text{-(CF}_2\text{)}_n\text{-O-CF=CF}_2$ (where n is 0, 1, or 2),
- 20 hexafluoropropylene, and perfluorobutylethylene.
3. A binder for electrode materials as set forth in Claim 1, wherein said tetrafluoroethylene based polymer has an average particle size of about 0.10 to about 0.18 μm .
- 25 4. A binder for electrode materials as set forth in Claim 1, wherein said tetrafluoroethylene based polymer has a standard specific gravity of about 2.12 to about 2.19.
- 30 5. A binder for electrode materials as set forth in Claim 1, wherein said tetrafluoroethylene based polymer has an extrusion pressure of about 270 kg/cm² or greater.
- 35 6. A process for making an electrode comprising:
 mixing electrode materials with a binder to form an electrode/binder mixture, said binder comprising tetrafluoroethylene based polymer fine particles having an average particle size of not more than about 0.20 μm and having a standard specific gravity of not more than about 2.20,

wherein a mixture prepared from said fine particles with about 17% by weight of the total mixture of an extrusion coagent, when subjected to the measurement of an extrusion pressure by a rheometer, exhibits under the conditions of a draw ratio of 100 to 1 and an extrusion speed of 18 ± 2 mm/min, an extrusion pressure of not less than about 220 kg/cm^2 ; and molding said electrode/binder mixture into an electrode.

7. A process for making an electrode as set forth in Claim 6, wherein said tetrafluoroethylene based polymer is polytetrafluoroethylene or a copolymer of tetrafluoroethylene with at least one comonomer selected from the group consisting of fluoro(alkyl vinyl ethers) represented by formula $\text{CF}_3\text{-(CF}_2\text{)}_n\text{-O-CF=CF}_2$ (where n is 0, 1, or 2), hexafluoropropylene, and perfluorobutylethylene.

8. A process for making an electrode as set forth in Claim 6, wherein said tetrafluoroethylene based polymer has an average particle size of about 0.10 to about $0.18 \text{ }\mu\text{m}$.

9. A process for making an electrode as set forth in Claim 6, wherein said tetrafluoroethylene based polymer has a standard specific gravity of about 2.12 to about 2.19.